

API 5L X65

- Production Standard of API 5L X65
- Dimensions and Sizes of API 5L X65
- Chemical Composition of API 5L X65
- Mechanical Properties Tensile Strength and Yield Strength of API 5L X65



Production Standard of API 5L X65

● API 5L X65

API 5L X65 line pipe is a petroleum and natural gas transport supply pipeline. The material for the API 5L X65 line pipe is steel grade. The pipeline is mostly used in the petroleum and oil and gas industries. With this being said, the API 5L X65 material gives the pipeline a very high resistance to crack propagation.

● Dimensions and Sizes of API 5L X65

NPS		O. D. mm	W. T.														
D N	Inc h		SCH 5S	SCH 10S	SCH 10	SCH 20	SCH 30	SCH 40	SCH 60	SCH 80	SCH 100	SCH 120	SCH 140	SCH 160	Sth	XS	XXS
50	2"	60.3	1.65	2.77	–	–	–	3.91	–	5.54	–	–	–	8.74	3.91	5.54	11.07
65	2 1/2"	73	2.11	3.05	–	–	–	5.16	–	7.01	–	–	–	9.53	5.16	7.01	14.02

80	3"	88.9	2.11	3.05	-	-	-	5.49	-	7.62	-	-	-	11.13	5.49	7.52	15.24
90	3 1/2"	101.6	2.11	3.05	-	-	-	5.74	-	8.08	-	-	-	-	5.74	8.08	-
100	4"	114.3	2.11	3.05	-	-	-	6.02	-	8.58	-	11.13	-	13.49	6.02	8.56	17.12
125	5"	141.3	2.77	3.4	-	-	-	6.55	-	9.53	-	12.7	-	15.88	6.55	9.53	18.05
150	6"	168.3	2.77	3.4	-	-	-	7.11	-	10.97	-	14.27	-	18.26	7.11	10.97	21.95
200	8"	219.1	2.77	3.76	-	6.35	7.04	8.18	10.31	12.7	15.09	18.26	20.62	23.01	8.18	12.7	22.23
250	10"	273.1	3.4	4.19	-	6.35	7.8	9.27	12.7	15.09	18.26	21.44	25.4	28.58	9.27	12.7	25.4
300	12"	323.9	3.96	4.57	-	6.35	8.38	10.31	14.27	17.48	21.44	25.4	28.58	33.32	9.53	12.7	25.4
350	14"	355.5	3.96	4.78	6.35	7.92	9.53	11.13	15.09	19.05	23.83	27.79	31.75	35.71	9.53	12.7	-
400	16"	406.4	4.19	4.78	6.35	7.92	9.53	12.7	16.66	21.44	26.19	30.96	36.53	40.49	9.53	12.7	-
450	18"	457.2	4.19	4.78	6.35	7.92	11.13	14.27	19.05	23.83	39.36	34.93	39.67	45.24	-	-	-
500	20"	508	4.78	5.54	6.35	9.53	12.7	15.09	20.62	26.19	32.54	38.1	44.45	50.01	-	-	-
550	22"	558.8	4.78	5.54	6.35	9.53	12.7	-	22.23	28.58	34.93	41.28	47.63	53.98	-	-	-
600	24"	609.6	5.54	6.35	6.35	9.53	14.27	17.48	24.61	30.96	38.89	46.02	52.37	59.54	-	-	-

●Chemical Composition of API 5L X65

- Chemical Composition for API 5L X65 PSL 1 pipe with $t \leq 0.984$ "

API 5L PIPE PSL1	Chemical Composition				Mechanical Property			
	C (Max)	Mn (Max)	P (Max)	S (Max)	TENSILE (Min)		YIELD (Min)	
					Psi X 1000	Mpa	Psi X 1000	Mpa
Grade X65	0.26	1.45	0.03	0.03	77	531	65	448

- a. $Cu \leq 0.50\%$; $Ni \leq 0.50\%$; $Cr \leq 0.50\%$; and $Mo \leq 0.15\%$,
- b. For each reduction of 0.01% below the specified maximum concentration for carbon, an increase of 0.05% above the specified maximum concentration for Mn is permissible, up to a maximum of 1.65% for grades $\geq L245$ or B, but $\leq L360$ or X52; up to a maximum of 1.75% for grades $> L360$ or X52, but $< L485$ or X70; and up to a maximum of 2.00% for grade L485 or X70.,
- c. Unless otherwise agreed $Nb + V \leq 0.06\%$,
- d. $Nb + V + Ti \leq 0.15\%$,
- e. Unless otherwise agreed.,
- f. Unless otherwise agreed, $Nb + V = Ti \leq 0.15\%$,
- g. No deliberate addition of B is permitted and the residual $B \leq 0.001\%$

- Chemical Composition for API 5L X65 PSL 2 Pipe with $t \leq 0.984$ "

Steel Grade	API 5L X52 Mass fraction, % based on heat and product analyses										Carbon Equiv a	
	C	Si	Mn	P	S	V	Nb	Ti	Other	CE IIW	CE Pcm	
	max b	max	max b	max	max	max	max	max		max	max	
Welded Pipe												
X65M	0.12	0.45	1.6	0.025	0.015	g	g	g	h,l	0.43	0.25	

- a. SMLS $t > 0.787$ ", CE limits shall be as agreed. The CEIIW limits applied if $C > 0.12\%$ and the CEPcm limits apply if $C \leq 0.12\%$,
- b. For each reduction of 0.01% below the specified maximum for C, an increase of 0.05% above the specified maximum for Mn is permissible, up to a maximum of 1.65% for grades $\geq L245$ or B, but \leq

L360 or API 5L X52; up to a maximum of 1.75% for grades > L360 or X52, but < L485 or X70; up to a maximum of 2.00% for grades ≥ L485 or X70, but ≤ L555 or X80, and up to a maximum of 2.20% for grades > L555 or X80.,

c. Unless otherwise agreed Nb = V ≤ 0.06%,

d. Nb = V = Ti ≤ 0.15%,

e. Unless otherwise agreed, Cu ≤ 0.50%; Ni ≤ 0.30% Cr ≤ 0.30% and Mo ≤ 0.15%,

f. Unless otherwise agreed,

g. Unless otherwise agreed, Nb + V + Ti ≤ 0.15%,

h. Unless otherwise agreed, Cu ≤ 0.50% Ni ≤ 0.50% Cr ≤ 0.50% and MO ≤ 0.50%,

i. Unless otherwise agreed, Cu ≤ 0.50% Ni ≤ 1.00% Cr ≤ 0.50% and MO ≤ 0.50%,

j. B ≤ 0.004%,

k. Unless otherwise agreed, Cu ≤ 0.50% Ni ≤ 1.00% Cr ≤ 0.55%, and MO ≤ 0.80%,

l. For all API 5L X52 PSL 2 pipe grades except those grades with footnotes j noted, the following applies. Unless otherwise agreed no intentional addition of B is permitted and residual B ≤ 0.001%.

●Mechanical Properties Tensile Strength of API 5L X65

- Mechanical Properties for API 5L X65 PSL-1 Pipe

Pipe Grade	Tensile Properties – Pipe Body of SMLS and Welded Pipes PSL 1			Seam of Welded Pipe
	Yield Strength a	Tensile Strength a	Elongation	Tensile Strength b
	Rt0,5 PSI Min	Rm PSI Min	(in 2in Af % min)	Rm PSI Min
X65	65,300	77,500	c	77,500

a. For intermediate grade, the difference between the specified minimum tensile strength and the specified minimum yield for the pipe body shall be as given for the next higher grade.

b. For the intermediate grades, the specified minimum tensile strength for the weld seam shall be the same as determined for the body using footnote a.

c. The specified minimum elongation, Af, expressed in percent and rounded to the nearest percent, shall be determined using the following equation:

$$Af = C \frac{A_{x0.2}^{0.2}}{U_{0.9}}$$

Where C is 1940 for calculation using Si units and 625 000 for calculation using USC units

Axc is the applicable tensile test piece cross-sectional area, expressed in square millimeters (square inches), as follows
– For circular cross-section test pieces, 130mm ² (0.20 in ²) for 12.7 mm (0.500 in) and 8.9 mm (.350 in) diameter test pieces; and 65 mm ² (0.10 in ²) for 6.4 mm (0.250in) diameter test pieces.
– For full-section test pieces, the lesser of a) 485 mm ² (0.75 in ²) and b) the cross-sectional area of the test piece, derived using the specified outside diameter and the specified wall thickness of the pipe, rounded to the nearest 10 mm ² (0.10in ²)
– For strip test pieces, the lesser of a) 485 mm ² (0.75 in ²) and b) the cross-sectional area of the test piece, derived using the specified width of the test piece and the specified wall thickness of the pipe, rounded to the nearest 10 mm ² (0.10in ²)
U is the specified minimum tensile strength, expressed in megapascals (pounds per square inch)

- Mechanical Properties for API 5L X65 PSL-2 Pipe

Pipe Grade	Tensile Properties – Pipe Body of SMLS and Welded Pipes PSL 2					Seam of Welded Pipe	
	Yield Strength a		Tensile Strength a		Ratio a, c	Elongation	Tensile Strength d
	Rt0,5 PSI Min		Rm PSI Min		R10,5IRm	(in 2in) Af %	Rm (psi)
	Minimum	Maximum	Minimum	Maximum	Maximum	Minimum	Minimum
X65Q, X65M	65,300	87,000	77,600	110,200	0.93	f	76,600

a. For intermediate grade, refer to the full API 5L specification.

b. for grades > X90 refers to the full API5L specification.

c. This limit applies for pipes with D> 12.750 in

d. For intermediate grades, the specified minimum tensile strength for the weld seam shall be the same value as was determined for the pipe body using foot a.

e. for pipe requiring longitudinal testing, the maximum yield strength shall be ≤ 71,800 psi

f. The specified minimum elongation, Af, expressed in percent and rounded to the nearest percent, shall be determined using the following equation:

$$Af = C \frac{A_{xc}^{0.2}}{U_{0.9}}$$

Where C is 1 940 for calculation using Si units and 625 000 for calculation using USC units

A_{xc} is the applicable tensile test piece cross-sectional area, expressed in square millimeters (square inches), as follows

– For circular cross-section test pieces, 130mm² (0.20 in²) for 12.7 mm (0.500 in) and 8.9 mm (.350 in) diameter test pieces; and 65 mm² (0.10 in²) for 6.4 mm (0.250in) diameter test pieces.

– For full-section test pieces, the lesser of a) 485 mm² (0.75 in²) and b) the cross-sectional area of the test piece, derived using the specified outside diameter and the specified wall thickness of the pipe, rounded to the nearest 10 mm² (0.10in²)

– For strip test pieces, the lesser of a) 485 mm² (0.75 in²) and b) the cross-sectional area of the test piece, derived using the specified width of the test piece and the specified wall thickness of the pipe, rounded to the nearest 10 mm² (0.10in²)

U is the specified minimum tensile strength, expressed in megapascals (pounds per square inch

g. Lower values fo R10,5IRm may be specified by agreement

h. for grades > x90 refers to the full API5L specification.